

POLYRESIN CLASSIC DARK GREY TEST RESULTS



TACTILE GROUND SURFACE INDICATOR (DISCRETE)

RANGE	Polyresin Classic
GROUP	Warning Tactile
MATERIAL	Dark grey virgin and re-claimed UV and thermally stabilized high impact elastomeric based polymers
FINISH	Mill finish
SUBSTRATE	As to particular product/substrate type recommendation
FIXING	As to particular method for product/substrate type recommendation

FEATURES

Engraved, concentric circle design on horizontal face with smooth outer edge

Manufactured in Australia from virgin and re-claimed UV and thermally stabilized high impact elastomeric based polymers

Unique integrated 'HEX' shaft design for substrate mounting (patents and design registrations applied and granted)

Tested for compliance with AS/NZS 1428.4: [1992 & 2002]

Tested for compliance with the BCA Section D clause 3.8 (TGSIs)

Tested for compliance with slip resistance requirements as detailed in HB 197 (1999)

5 year on polymer for colour stability (polymer), 2 year installation warranty

DTAC's facility to reclaim, recycle and reinstate

SLIP RESISTANCE TESTING

Important information about slip resistance ratings: To determine a classification of a slip resistance rating, see Australian Standards Hand Book 197: 1999 (HB 197), An Introductory Guide to Slip Resistance of Pedestrian Materials. This document outlines the minimum ratings of a location and situation of a pedestrian surface.

TEST	AS/NZS 4586:1999 APPENDIX A
TYPE	Wet Pendulum Test
RATING 1	Four S Slider = 46
RATING 2	TRRL Slider = 36
CLASS	Mean BPN = Class N/A
REPORT	(Intertile Pty Ltd test report) Available on request from DTAC

LUMINANCE TESTING

Important information: To determine a luminance contrast between a substrate and the DTAC TGSi node, see: AS/NZS 1428.4 2002, page 51-59, appendix F. As the testing for luminance is performed only on the 25mm face of the TGSi (test report), INSAFE product IS-AS-PL-DARK GREY has been applied to this product. The colour of the disc insert (25mm) would fall within the mean luminance rating.

TEST	AS 1428:4 2002 APPENDIX F
TYPE	Access for people with disabilities
RATING	Luminance Reflectance rating / Dry, Wet & Mean TBA
REPORT	(Test report N/A)

MELBOURNE SYDNEY	CANBERRA BRISBANE ADELAIDE	PERTH DARWIN HOBART
DTAC PTY LTD ABN 41 093 070 127	Unit 4, 1-7 Friars Road Moorabbin Victoria Australia 3189 PO Box 2210 Moorabbin Victoria Australia 3189	T 1300 793 478 F 1300 780 628 estimating@dtac.com.au www.dtac.com.au

POLYRESIN CLASSIC DARK GREY INSTALLATION


DTAC PTY LTD
ABN 41 093 070 127

Unit 4, 1-7 Friars Road
Moorabbin Victoria
Australia 3189
PO Box 2210
Moorabbin Victoria
Australia 3189

T 1300 793 478
F 1300 780 628
estimating@dtac.com.au
www.dtac.com.au

TYPE 1 SUBSTRATES


STONE, MASONRY, TIMBER, VINYL



CODE	BS-PL-M8x18-HEX-PF-DARKGREY
FIXING	Drill and pressure fit
NOTE	Any thick substrate where maximum hold is required without chemical anchoring
GREEN	100% recyclable, no adhesives

TYPE 2 SUBSTRATES


VITRIFIED PORCELAIN, CERAMICS, GLASS, METALS



CODE	BS-PL-M8x18-HEX-PF-DARKGREY
FIXING	Diamond core/pressure fit
NOTE	Any thick substrate where maximum hold is required without chemical anchoring
GREEN	100% recyclable, no adhesives

TYPE 3 SUBSTRATES

CARPET, CARPET TILES



CODE	BS-PL-M8x18-HEX-PF-DARKGREY
FIXING	Drill and pressure fit
NOTE	Thin carpet without underlay (direct stick carpet/carpet tiles). Two stage installation process
GREEN	100% recyclable, no adhesives